


# Ergitan® 3.7035 (Grade 2) Data Sheet

## CAD/CAM Blanks dental

### Medical Alloys



Zapp is Certified to ISO 9001



#### Ergitan® 3.7035

Ergitan® 3.7035 is an unalloyed pure titanium. This material has an exceptional biocompatibility and is accepted by the human body because of its non-toxic and non-allergic elements. CAD/CAM blanks are available from stock or can be produced acc. to customer-specific drawings.

#### Typical fields of application

- Crowns
- Bridges
- Individual designed constructions

#### Corresponding standards

- ASTM F67 (UNS R50400)

#### Guideline

- Following DIN EN ISO 22674:2006

#### Magnetism

Ergitan® 3.7035 is not magnetizable.

#### Corrosion resistance

Ergitan® 3.7035 is characterized by an extraordinary corrosion resistance because of the low Fe content. This material also has a high resistance against pitting corrosion. Due to the formation of a dense oxide layer Ergitan® 3.7035 shows good corrosion resistance in an oxidizing environment.

#### Machining

In annealed condition, machinability of Ergitan® 3.7035 is good. In comparison to high quality steels, the cutting rate of Ergitan® 3.7035 should be reduced. It is important to ensure very good cooling.

#### Chemical composition \*

Fe	O	H	C	N	Ti
max. 0.30	max. 0.25	max. 0.015	max. 0.08	max. 0.03	Bal.

\* Average in mass -%

#### Mechanical properties

Tensile Strength	[MPa]	min. 345
Yield Strength	[MPa]	min. 275

#### Physical properties

Modulus of Elasticity E at 20 °C [GPa]	105
Specific Density [kg/dm³]	4.5
Thermal Conductivity at 20 °C [W/m*K]	22
CTE Coefficient of Thermal Expansion [10 <sup>-6</sup> *K <sup>-1</sup> ] 25 - 500 °C	9.6
Specific Heat at 20 °C [kJ/kg*°C]	526
Electric Resistivity ρ at 20 °C [Ω*mm²/m]	0.48

**Delivery conditions\***

Range of Dimension	98 – 100 mm
Finish	Processed surface
Shape	<input type="checkbox"/> Round <input type="checkbox"/> Round with step <input type="checkbox"/> Acc. to drawing
Thickness	8.00 10.00 12.00 13.50 14.00 15.00 16.00 17.50 18.00 20.00 ... up to 28.00
Service Conditions	<input type="checkbox"/> Labeled or laser marked on demand <input type="checkbox"/> Single or multiple packing units

\* All others on request

**Zapp Precision Metals GmbH**

MEDICAL ALLOYS

Letmather Straße 69

58239 Schwerte

P.O. Box 17 20

58212 Schwerte

Phone +49 2304 79-540

Fax +49 2304 79-482

[medicalalloys@zapp.com](mailto:medicalalloys@zapp.com)[www.zapp.com](http://www.zapp.com)

Further information regarding our products and locations are available in our image brochure and under [www.zapp.com](http://www.zapp.com)

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.  
Last revision: July 2020