


Ergste® 1.4104YN Datasheet US

Medical Alloys



Zapp is Certified to ISO 9001



Ergste® 1.4104YN

Ergste® 1.4104YN is a martensitic stainless steel with 17% of Chromium content. Due to the high content of Sulfur an increased machinability is achieved. On the other hand, this leads to both decreased corrosion resistance and ductility. Ergste® 1.4104YN shows a good resistance to rust and acid. Further, it is possible to improve the mechanical resistance because of the carbon content. The improvement can be achieved by quenching and tempering.

Typical Applications

- Surgical instruments
- Decorative purposes
- Construction parts that show resistance in water and steam environments
- General machine and apparatus parts
- Piston rods for pneumatic cylinders

Weldability

Generally, Ergste® 1.4104YN is not welded. The material is particularly unsuitable for joint welding. If welded, it is recommended to finish with a heat treatment to ensure the equality of the mechanical-technological properties in the welding zone and the base material

Polishability

Ergste® 1.4104YN is not suitable for polishing.

Magnetism

Ergste® 1.4104YN is magnetizable.

Corrosion Resistance

Ergste® 1.4104YN has a worse corrosion resistance than Ergste® 1.4016IH. The resistance to chlorinated media is impaired due to high content of sulfur. Plus, media that cause pitting and crevice corrosion should be avoided.

Corresponding Standards

- _ according to DIN EN 10088-3 (X14CrMoS17)
- _ according to AISI 430F

Chemical Composition

	C	Si	Mn	Cr	Mo	P	S
Min.	0.10	0	0	15.5	0.2	0	0.15
Max.	0.17	1.0	1.5	17.5	0.6	0.04	0.35

Mechanical Properties (Solution-Annealed)

Tensile Strength	TS/[ksi]	max. 105
Hardness	HB	max. 220

Mechanical Properties (Quenched and Tempered)

Tensile Strength	TS/[ksi]	94.5 – 123
Yield Strength	YS _{0.2} /[ksi]	min. 72.5
Elongation at break, t ≤ 60 mm	A ₅ /[%]	min. 12
Elongation at break, 60 mm < t ≤ 160 mm	A ₅ /[%]	min. 10

Physical Properties

Modulus of Elasticity at 68 °F	E/[ksi]	31,183
Density	ρ/[lb/in ³]	0.28
Thermal Conductivity at 68 °F	λ [Btu in/hr ft ² °F]	173.3
Coefficient of Thermal Expansion	α [μin/in °F]	
68 – 212 °F		5.6
68 – 392 °F		5.8
68 – 572 °F		5.8
68 – 752 °F		5.8
Specific Heat at 68 °F	c/[Btu/lb °F]	0.11
Specific Electric Resistivity at 68 °F	ρ/[Ωcircular mil/ft]	421.7

Hot Working

Hot working is to be performed at temperatures between 1,472 °F and 2,012 °F. Start with slow heating to approximately 1,562 °F.

Cooling in Air.

Cold Working

Ergste® 1.4104YN is not suitable for cold working because of the sulfur precipitation.

Machining

The machining of Ergste® 1.4104YN is better in comparison to other steels with 17% content of chrome. The reason for that is the increased content of sulfur.

Heat Treatment**Soft Annealing**

Temperature: 1,382 °F – 1,562 °F

Cooling: Oven, Air

Hardening

Temperature: 1,742 °F – 1,958 °F

Cooling: Quickly enough in oil, air

Tempering

Temperature: 1,022 °F – 1,202 °F

Cooling : Air

Zapp Precision Metals GmbH

MEDICAL ALLOYS

Letmather Straße 69

58239 Schwerte

P.O. Box 17 20

58212 Schwerte

Phone +49 2304 79-540

Fax +49 2304 79-482

medicalalloys@zapp.com

www.zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.

Last revision: July 2020