

1.4105 IL, AISI 430FR, X6CRMOS17 WIRE

Automotive & Automation, Data Sheet US



Zapp is certified to ISO 9001 | IATF 16949



Categorization Alloy 1.4105 IL from Zapp

- Ferritic, corrosion resistant steel
- DIN EN 10088-3
- ASTM 838, Alloy Type 2 Grade 1
- AISI 430FR
- X6CrMoS17 (similar)

[Information about further automotive applications at Zapp](#)

Typical Applications of 1.4105 IL

Our material Ergste® 1.4105 IL is mainly used in solenoid valves for pneumatic, hydraulic and HVAC applications.

Processing and Usage Properties

Ergste® 1.4105 IL (similar to X6CrMoS17) is a stainless free cutting steel with excellent soft magnetic properties. It is designed for the volume production of precision turned parts. The grade is resistant in water, steam and other less aggressive media.

If welding is necessary, plasma- or laser welding should be preferred. The steel is suitable for cold forming operations within certain limits.

For improved properties in selective cases we recommend the following Ergste® grades:

Cold Heading

Ergste® 1.4003 IA
Ergste® 1.4016 IM

Corrosion Resistance

Ergste® 1.4113 IM

Machinability

Ergste® 1.4105 IM
Ergste® 1.4523 IM

Typical chemical Analysis*

C	Si	Mn	S	Cr	Mo
≤ 0.03	1.0-1.5	≤ 0.8	0.25-0.35	17.25-18.00	0.20 - 0.50

* weight percentage / approximate value

Mechanical and Physical Properties

Tensile strength (soft annealed)	350- 550 MPa
----------------------------------	--------------

Magnetic Properties of Round Bars

∅ 3.8 – 6.7 mm

Coercitive strength H_c	≤ 220 A/m
Maximum relative permeability μ_{max}	≥ 1,200
Saturation polarization J_s	≥ 1.5 T
Remanence B_r	0.5 - 1.1 T
Specific el. resistance ρ	≥ 0.79 $\mu\Omega m$

∅ 6.8 – 27.0 mm

Coercitive strength H_c	≤ 180 A/m
Maximum relative permeability μ_{max}	≥ 1,700
Saturation polarization J_s	≥ 1.5 T
Remanence B_r	0.5 - 1.1 T
Specific el. resistance ρ	≥ 0.79 $\mu\Omega m$

Delivery Forms

Round bars	annealed, ground
Profiles	annealed, straightened

Surface Finish

Crack tested according to DIN EN 10277, surface class 1-4

[Information about further stainless steel alloys at Zapp.](#)

Magnetic Properties

Ergste® 1.4005 IA

Ergste® 9.9013 IL

Weldability

Ergste® 1.4511 IA

[Further information: Please see our linecard for precision wire products.](#)

Zapp Precision Metals GmbH

PRECISION WIRE

Letmather Straße 69

58239 Schwerte

Phone +49 2304 79-7469

Fax +49 2304 79-67469

precisionwire@zapp.com

www.zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The data sheet is not subject to change control.

Last revision: August 2022