# M42 - 1.3247 - High Speed Steel Data Sheet - Tooling Alloys



## Zapp is certified to ISO 9001













# Key Features of Zapp's High Speed Steel M42 - 1.3247:

- O HSS 2-9-1-8
- Cobalt alloyed high speed steels
- High thermal stability and high wear resistance
- o Case hardness up to 68 HRC possible

## Typical Areas of Application

Cutting Tools

## Physical properties

Modulus of elasticity E [GPa]	220
Density [kg/dm³]	8,0
Thermal expansion coefficient [mm/(mm/K] in a temperature range up to 400 °C	11,6 x 10 <sup>-6</sup>


## Delivery condition

As-delivered condition	Soft-annealed, approx. 280 HB
Product form	Round bars, flat bars
Surface finish	Mechanically machined

#### Typical chemical composition (wieght-%)

С	Cr	Мо	W	V	Co
1,1	3,9	9,4	1,5	1,1	7,8

## Tempering diagram



## **Heat Treatment**

# **Soft Annealing**

- In neutral atmosphere at ~ 830 °C and ~ 4 h exposure time (after through-heating)
- Followed by furnace cooling
- Soft annealing hardness ~ 280 HB

## Stress Relief Annealing

 $\sim 650\,^{\circ}\text{C}/\sim 2~h$  exposure time (after through-heating) followed by furnace cooling

You can find more materials at: www.zapp.com/en-uk/materials/powder-metallurgical-tool-steel

Zapp Precision Metals GmbH ensures professional execution of all heat treatment steps as well as their preparation and post-processing (e.g., charging, hardness testing, straightening processes, etc.) – always with the aim of obtaining the optimum component properties!

We are happy to assist you with constructive advice!

## TOOLING ALLOYS

Zapp Precision Metals GmbH Balcke-Dürr-Allee 1 40882 Ratingen Phone +49 2304 79-566 Sales.TA@zapp.com www.zapp.com Further information regarding our products and locations are available in our image brochure and on our homepage at www.zapp.com

The information, illustrations, drawings, dimensional and weight data, and other data included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the materials. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. This brochure is not subject to change control. Subject to prior sale. Last revision: July 2023