


Slicklines Zapp-SW Stainless Wire



Zapp is certified to ISO 9001



Slicklines

Wire for slicklines in a wide range of stainless steels and high-alloy materials, suitable for both sour and sweet wells. Zapp's wide range for single-strand slicklines makes it possible to select the most appropriate grade for a specific environment. This contributes to safer operations and longer service life.

Failure Analysis

Zapp is capable of carrying out comprehensive slickline material failure analyses.

Cut Costs With Stainless Steel Slicklines

Although a higher initial cost, stainless steel slicklines can provide significant savings compared to carbon steel slicklines, which are more susceptible to failure and lost production time.

Even in wells of moderate corrosive conditions, a stainless steel or high-alloy slickline will provide a significantly longer life, meaning:

- _ Less downtime in the well
- _ Fewer slicklines to be purchased
- _ Fewer slicklines to be re-spoiled

Slickline Materials

Zapp’s program of wire for slicklines includes stainless steels and high-alloy materials, suitable for both sour and sweet wells. Other grades can be offered on request.

Carbon steel	Description
Zapp C276-SW (UNS N10276)	A lead-free, hardenable, free-cutting carbon steel characterized by excellent machinability, high hardness, high wear resistance and exceptional dimensional stability after hardening.
Zapp 26Mo (UNS N08926)	For service in sour oil and gas wells. Very good resistance to stress corrosion cracking (SCC) in H ₂ S, chloride and CO ₂ environments. Very good resistance to pitting and general corrosion. Breaking loads are high. Also suitable as armor wire for multi-strand logging cables.
Zapp 28 (UNS N08028)	For service in high-temperature sour oils and gas wells. Very good resistance to stress corrosion cracking (SCC) in H ₂ S, chloride and CO ₂ environments. Very good resistance to pitting and general corrosion.
Zapp 2507-SW (UNS S32750)	For service in highly corrosive oil and gas wells. Excellent resistance to stress corrosion cracking (SCC) in chloride and CO ₂ environments. Excellent resistance to pitting and general corrosion in chloride and acidizing environments. Breaking loads are very high.
Zapp 2505-SW (UNS S32205)	For service in corrosive oil and gas wells. High resistance to stress corrosion cracking (SCC) in chloride and CO ₂ environments. High resistance to pitting and general corrosion.
Zapp 316L-SW (UNS S31600, ASTM 316)	For service in less severe corrosive oil and gas wells. Good resistance to general corrosion.
Zapp CS9A-SW	A high-strength carbon steel suitable for use in sweet oil and gas wells.

Slickline Lengths*

Wire size, (in.)	Maximum length, ft (approx..)	Maximum length, m (approx..)
0.082	70000	27000
0.092	55000	17000
0.108	40000	12000
0.125	35000	11000
0.140	30000	9000
0.150	30000	9000
0.160	25000	7600

* Zapp’s materials for slickline wire is supplied in lengths according to the table.

Sizes and Breaking Loads

The table shows Zapp's program of slickline standard sizes. Slickline wire is supplied on metallic spools and in specified continuous lengths.

Grade (UNS)	Diameter, in.	Minimum breaking load, lbf
Zapp C276-SW (UNS N10276)	0.108	2391
	0.125	3204
Zapp 26Mo (UNS N08926)	0.082	1214
	0.092	1530
	0.108	2105
	0.125	2820
	0.150	4061
Zapp 28 (UNS N08028)	0.160	4621
	0.082	1149
	0.092	1446
	0.108	1992
	0.125	2669
Zapp 2507-SW (UNS S32750)	0.150	3843
	0.160	4373
	0.092	1735
	0.108	2391
	0.125	3203
Zapp 2205-SW (UNS S32205)	0.140	4018
	0.150	4357
	0.082	1302
	0.092	1639
	0.108	2258
Zapp 316L-SW (UNS S31600, ASTM 316)	0.125	3025
	0.140	3795
	0.150	4356
	0.160	4665
	0.082	1149
Zapp CS9A-SW	0.092	1446
	0.108	1992
	0.125	2491
	0.150	3587
	0.160	4082
Zapp CS9A-SW	0.082	1475
	0.092	1856
	0.108	2558
	0.125	3427
	0.140	4129

Zapp Precision Metals (Sweden) AB

PRECISION WIRE

Järnverksleden 18

81 134 Sandviken

Sweden

Phone +46 26 191800

precisionmetals-sweden@zapp.com

www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.

Last revision: June 2020