


Ergste® 1.4197YU Datasheet US

Medical Alloys



Zapp is Certified to ISO 9001



Grade Ergste® 1.4197YU

Ergste® 1.4197YU is a sulfur-alloyed martensitic stainless steel with 13 % chromium content and high corrosion resistance. Due to the addition of sulfur machinability is improved. Furthermore, the element molybdenum induces a higher corrosion resistance in comparison with Ergste® 1.4035YU. In conducting an appropriate heat treatment, a maximum hardness of 53 HRC* can be achieved.

Typical Fields of Application

- Dental Instruments, e.g. Milling Cutters, Drills
- Surgical Instruments e.g. Cutting Tools
- Surgical Needles
- Watchmaking industry

Weldability

Weldability of Ergste® 1.4197YU is possible to a limited extent.

Solderability

Soft-soldering is possible.

Magnetism

Ergste® 1.4197YU is magnetizable.

Cold Working

In the soft-annealed condition.

Machining

Best results can be achieved in a slightly cold-worked condition ($116 \leq TS \leq 138$ ksi).

* Maximum hardness achievable under ideal hardening conditions

Corresponding Standards

- X20CrNiMoS13-1
- 420F Mod acc. to ASTM F899

Typical Chemical Composition*

C	Si	Mn	Cr	Mo	S	Ni
0.23	0.50	1.00	14.00	1.30	0.21	1.10

* Average in mass-%

Mechanical Properties (Soft-Annealed)

Tensile Strength TS	[ksi]	94.3 – 123.3
Yield Strength YS	[ksi]	min. 58.0
Elongation A5	[%]	max. 25
Hardness HB		max. 262
Structure		Ferrite + Carbides

Mechanical Properties (Cold-Worked)

Tensile Strength TS	[ksi]	116.0 – 152.3
Yield Strength YS	[ksi]	max. 116.0

Physical Properties

Modulus of Elasticity E 70 °F	[ksi]	31,183
Specific Density	[lb/in³]	0.28
Thermal Conductivity 70 °F	[Btu in/hr ft² °F]	208.0
Coefficient of Thermal Expansion	[µin/in °F]	
70 - 210 °F		5.8
70 - 390 °F		6.1
70 - 570 °F		6.4
70 - 750 °F		6.7
Specific Heat 70 °F	[Btu/lb °F]	0.11
Electric Resistivity 70 °F	[Ω circular-mil/ft]	330.8

Hot Working

Forging temperature is 1,470 – 1,920 °F.
Heat slowly and gradually to approx. 1,470 °F.
Afterwards heat to the required forging temperature.
Cool slowly after forging (e.g. in furnace).

Heat Treatment

Soft Annealing

Temperature: approx. 1,435 °F
Holding time: 2 - 4 h
Cooling: furnace


Hardening

Temperature: 1,875 – 2,010 °F
Holding time: approx. 0.5 h (depending on cross-section)
Cooling: inert gas, oil

Tempering

Temperature: 210 - 570 °F
Holding time: approx. 1 h (depending on cross-section)
Cooling: air
Due to the 885 °F embrittlement tempering in this range should be avoided.

Tempering Chart



According to the required hardness and the actual dimension the hardening and tempering temperature have to be selected from the respective ranges.

Corrosion Resistance

The optimum corrosion resistance can be achieved in the hardened and tempered condition. The best precondition to accomplish the optimum corrosion resistance is electronic polishing followed by passivation treatment. In this condition Ergste® 1.4197YU is resistant against water and water vapour. Due to the higher molybdenum content Ergste® 1.4197YU shows a higher corrosion resistance in comparison with Ergste® 1.4035YU.

Zapp Precision Metals GmbH

MEDICAL ALLOYS
Letmather Straße 69
58239 Schwerte
P.O. Box 17 20
58212 Schwerte
Phone +49 2304 79-540
Fax +49 2304 79-482
medicalalloys@zapp.com

www.zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.

Last revision: July 2020