# Alloy Westig® 1.4006 Datasheet Precision Strip



Zapp is certified to ISO 9001

Westig® 1.4006 hardened and tempered

Material-No. 1.4006 according to EN 10088-2

Cold rolled, hardened and tempered

Edge finish

Slit

Surface finish

Polished

 $R_t \le 3.0 \ \mu m$ 

 $R_{\rm a} \leq 0.30 \; \mu m$ 

**Dimensions** 

Thickness: 0.10 - 1.50 mm

Width: 20 - 300 mm

**Flatness** 

Permissible deviation transverse to direction of rolling: Thickness ≥ 0.20 mm: max. 0.2 % of the strip's width

Thickness < 0.20 mm: max. 0.3 % of the strip's width

Straightness

max. 1.5 mm/1 m

Tensile strength

1,200 – 1,400 MPa dependent on dimension

Form of delivery

Coils

Inside diameter: 300/400 mm

Outside diameter: max. 1,000 mm

Coil weight: min. 40 kg

Information concerning minimum quantities and our capabilities to produce material with characteristics which differ from the above mentioned data are available upon request.

## Approximate chemical Analysis (%)

| С    | Mn     | Si     | P | S             | Cr   | Ni     |
|------|--------|--------|---|---------------|------|--------|
| 0.11 | ≤ 1.50 | ≤ 1.00 |   | max.<br>0.025 | 12.5 | ≤ 0.75 |

#### **Tolerances**

Width tolerances in mm (acc. to B1)

| Thickness (mm)   | Width (mm)   | Tolerances (mm) ± |
|------------------|--------------|-------------------|
| < 0.250          | < 20         | 0.07              |
|                  | 20 to < 50   | 0.10              |
|                  | 50 to < 125  | 0.15              |
|                  | 125 to < 250 | 0.20              |
|                  | 250 to 320   | 0.30              |
| 0.250 to < 0.500 | < 20         | 0.10              |
|                  | 20 to < 50   | 0.15              |
|                  | 50 to < 125  | 0.20              |
|                  | 125 to < 250 | 0.25              |
|                  | 250 to 320   | 0.35              |
| 0.500 to < 1.000 | < 20         | 0.15              |
|                  | 20 to < 50   | 0.20              |
|                  | 50 to < 125  | 0.25              |
|                  | 125 to < 250 | 0.30              |
|                  | 250 to 320   | 0.40              |
| 1.000 to < 1.600 | < 20         | 0.20              |
|                  | 20 to < 50   | 0.25              |
|                  | 50 to < 125  | 0.30              |
|                  | 125 to < 250 | 0.35              |
|                  | 250 to 320   | 0.45              |
| 1.600 to < 2.000 | < 20         | 0.25              |
|                  | 20 to < 50   | 0.30              |
|                  | 50 to < 125  | 0.35              |
|                  | 125 to < 250 | 0.40              |
|                  | 250 to 320   | 0.50              |

### Thickness tolerances in mm (acc. to T3)

| Thickness (mm)   | Tolerances (mm) ± |
|------------------|-------------------|
| 0.080 to < 0.125 | 0.004             |
| 0.125 to < 0.200 | 0.005             |
| 0.200 to < 0.250 | 0.006             |
| 0.250 to < 0.315 | 0.007             |
| 0.315 to < 0.400 | 0.008             |
| 0.400 to < 0.500 | 0.009             |
| 0.500 to < 0.630 | 0.010             |
| 0.630 to < 0.800 | 0.012             |
| 0.800 to < 1.000 | 0.013             |
| 1.000 to < 1.250 | 0.017             |
| 1.250 to < 1.600 | 0.020             |
| 1.600 to < 2.000 | 0.023             |
|                  |                   |

## Zapp Precision Metals GmbH

PRECISION STRIP
Hochstraße 32
59425 Unna
P.O. Box 21 29
59411 Unna
Phone +49 2304 79-508
Fax +49 2304 79-7979
precisionstrip@zapp.com
www.zapp.com

Further information regarding our products and locations are available in our image brochure and under www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.

Last revision: December 2019