


7C27 Datasheet

Medical Wire

Zapp is certified according to ISO 9001



Alloy 7C27

is a martensitic stainless chromium steel characterized by very good hardening properties and very good cold formability. After hardening and tempering, the grade has very good corrosion resistance and toughness.

7C27 is Characterized by

- Soft delivery condition
- Very good hardening properties
- Very good cold formability
- High corrosion resistance after hardening and Tempering

Applications

Alloy 7C27 can be used for surgical suture needles, dental burrs, drills and tartar removers.

Standards

- ASTM: 420
- AWS: ER 420
- EN Number: 1.4028 Mod./1.4031 Mod.
- W.Nr.: 1.4007
- DIN: X35Cr14
- SS: 2304
- AFNOR: Z 30C13(13H)

Product standards

- ASTM F899
- ISO 16061

Chemical Composition (nominal) %

C	Si	Mn	P	S	Cr
0.32	0.2	0.3	≤ 0.025	≤ 0.010	13.5

Forms of Supply

The wire is supplied coated with an anti-corrosion oil that should not be removed in storage. In cases where the first work operation is a straightening-cutting operation, the oil acts as an excellent lubricant and prevents scratching of the wire surface.

After the oil is removed, the wire should not be stored on premises with a high moisture content, since the material can be subject to corrosion in the unhardened state.

The wire surface is bright in diameters 0.10 - 2.50 mm (0.004 - 0.098 in.). Larger wire diameters can be manufactured on request.

Spools

Dimension		Spool no	Wire weight	
mm	in.		kg	lb
0.285 - 1.6	0.011 - 0.063	23.0	max. 16.0	max. 35.0

Coils, metric units

Dimension, mm	Inside diameter of coil, mm	Wire weight, kg
0.50 - 0.80	250	max. 16
> 0.80 - 1.60	300	max. 20
> 1.60 - 1.80	300	max. 20
> 1.80 - 2.50	450	approx. 60

Coils, imperial units

Dimension, in.	Inside diameter of coil, in.	Wire weight, lb
0.02- 0.031	9.8	max. 35
> 0.031 - 0.063	11.8	max. 44
> 0.063- 0.071	11.8	max. 44
> 0.071 - 0.098	17.7	approx. 132

In exceptional cases, spools or coils of lower weight than given in the above tables can be included in a delivery.

Tolerances

The diameter tolerance is normally D3. The wire can also be supplied with tolerance grades D1 and D2.

Metric units

Dimension, mm	Diameter tolerance, mm +/-		
	D1	D2	D3
0.10 - 0.125	0.007	0.004	0.002
> 0.125 - 0.25	0.009	0.005	0.003
> 0.25 - 0.50	0.011	0.007	0.004
> 0.50 - 1.00	0.014	0.009	0.005
> 1.00 - 1.60	0.018	0.011	0.006
> 1.60 - 2.50	0.023	0.014	0.008

Imperial units

Dimension, in	Diameter tolerance, in.		
	D1	D2	D3
0.004 - 0.005	0.00028	0.00016	0.00008
> 0.005 - 0.010	0.00035	0.00020	0.00012
> 0.010 - 0.020	0.00043	0.00028	0.00016
> 0.020 - 0.039	0.00055	0.00035	0.00020
> 0.039 - 0.063	0.00071	0.00043	0.00024
> 0.063 - 0.098	0.00091	0.00055	0.00032

Mechanical Properties

The wire is supplied in tensile strengths within the range shown in the table below. The smaller the diameter, the higher the tensile strength within the stipulated range.

Tensile strength, Rm	MPa (ksi)
	730 - 900 (106 - 131)

Other tensile strengths can be supplied on request.

Physical Properties

Density: 7.7 g/cm³, 0.28 lb/in³

Heat Treatment

Soft-annealing

When required, soft-annealing should be conducted for a period of one hour at a temperature of 650-680 °C (1,200-1,250 °F).

Hardening

Temperature, °C (°F)	1,050 - 1,080 (1,920 - 1,975)
Holding time, minutes	5 - 6

Quenching in oil or in protective gas.

To prevent oxidation, hardening should be carried out in a protective gas atmosphere using nitrogen or argon, alternatively in vacuum. The use of other gases can cause brittleness, blanks sticking together etc.

Tempering time, minutes	30
Temperature, °C (°F)	250 - 300 (480 - 570) Depending on the final hardness and ductility required

Zapp Precision Metals (Sweden) AB

PRECISION WIRE

Järnverksleden 18

811 34 Sandviken

Sweden

Phone +46 26 265467

precisionmetals-sweden@zapp.com

www.zapp.com

The illustrations, drawings, dimensional and weight data and other information included in this data sheet are intended only for the purposes of describing our products and represent non-binding average values. They do not constitute quality data, nor can they be used as the basis for any guarantee of quality or durability. The applications presented serve only as illustrations and can be construed neither as quality data nor as a guarantee in relation to the suitability of the material. This cannot substitute for comprehensive consultation on the selection of our products and on their use in a specific application. The brochure is not subject to change control.
Last revision: January 2020